

## PRODUCT INFORMATION

# DAIWAX BAP-1

— N,N'-Ethylene-bis(stearamide) —

### \* Specifications

Appearance	.....	White powder
Moisture	.....	Max. 1.0%
Melting Point	.....	140-150°C
Ash Content	.....	Max. 0.1%
Acid Value	.....	Max. 10.0mgKOH/g
Amine Value	.....	Max. 10.0mgKOH/g
Specific Gravity	.....	0.4-0.5g/ml
80 mesh on	.....	Trace
100 mesh pass	.....	Trace
145 mesh pass	.....	Min. 95.0%

### \* Uses

- Lubricant for powder metallurgy
- Most suitable for copper powder and stainless steel powder

### \* Characteristics

- High melting point wax.
- For powder metallurgy, and the surface of the sintered product is clean.
- Good release characteristics
- No contamination of the sintering furnace
- When mixing, less adhesion to mixer and spring liner

### \* Packaging

20kg carton box

**DAINICHI CHEMICAL INDUSTRY Co., Ltd.**

7-3-4, Nakaishikiri-cho, Higashiosaka-shi, Osaka-fu, 579-8014, Japan

TEL:072-985-1851 (60601)